



INTRODUCTION

No-Chip is a handmade panel containing natural materials and as such no two panels will be the same. Ensure that you familiarise yourself with the possible variation and storage conditions.

- 01 Each sheet may vary in colour, and have different, grain patterns, flecks, and other may have small inclusions such as pieces of wood. This will vary within a sheet and between sheets, samples are indicative only and may differ from finished sheets.
- 02 The sheet surface can contain small pores, indentations, or other small oddities as a result of our hand casting process. These are not considered defects and do not affect the performance of the surface.
- 03 Sheets can vary in both thickness and flatness :
eg. A sheet may be 21mm in one area, and 20mm in another.
eg. Overall flatness along length or width can vary from sheet to sheet.
- 04 Sheets should be stored at min 18°C and at a relative humidity of 35% - 65% wherever possible.
- 05 If stored in cold conditions Foresso sheets can bow or cup. This can occur in transit. Ensure that the sheets are given time to acclimatise to their environment and are stored as detailed above.



COMPOSITION

Material	Origin	Notes
Extraction Dust	UK	Collected in-house
Wood Dust/Planing Waste	UK	Sourced from SMEs in the UK
Mineral Powders	UK	50% sourced as waste
0% VOC Bio-based Epoxy Resin	UK	34% Biological Content
Pigment	UK	98% Biological Content
BB/BB Birch Plywood	EU	FSC & PEFC
Standard Hardwax Oil Finish	UK	Food-safe Natural Oil

MATERIAL PROPERTIES

COMPRESSIVE STRENGTH	Proportional Limit	10.31 MPa
	Strain at Limit	2.17 %
	Turning Point	13.10 MPa
	Strain at Turning Point	2.45 %
	Compression Modulus	892.46 MPa
FLEXURAL STRENGTH	Maximum Flexural Stress	77.06 MPa
	Strain at Break	1.78 %
	Flexural Modulus	5498.68 MPa
TOLERANCES	Thickness: 20mm	+/- 0.5 mm
	Length and Width (Sheets) Sheets are supplied with a factory edge and can include slightly rounded corners/ends	+/- 10 mm
	Length and Width (Flooring/CNC)	+/- 1 mm



FINISHES

Name	Standard	Description
Hardwax Oil	EN71-3: 2013	Food safe natural worktop oil with high resistance to scratching and staining.
High Traffic Furniture Lacquer	FIRA 6250:2005	Horizontal surfaces in Heavy/Severe contract usage
High Traffic Floor Lacquer	2004/42/EC	Medium to High traffic lacquer for wooden floors in commercial and insitutional environments.
Anti-slip Floor Lacquer	2004/42/EC BS 7976-2	Reduces slip potential in bars, schools, shopping centres, and all other high traffic public areas.
Fire Rated Lacquer	BS476 Part 6	Fire Propagation of Products Report Number: 315455
	BS476 Part 7	Surface Spread of Flame of Products Report Number: 315456
	EN13501-1	"Euro" Classification B-s1,d0 Report Number 333923
	FIRA 6250:2005	Horizontal surfaces in Heavy/Severe contract usage